



# Salt Spray Corrosion Test Chamber

-----Internal dimension can be customized

-----Continuous and programmable spraying

Name	Salt Spray Corrosion Chamber		
Model	SH-90	SH-120	SH-160
Internal Dimension WxHxD (mm)	900x500x600	1200x500x800	1600x500x800
External Dimension WxHxD (mm)	1400x1200x900	2100x1400x1300	2300x1400x1300
Lab Temperature	Saline test (NSS ACSS) 35±1 °C ;Corrosion Test (CASS)50±1 °C		
Pressure Bucket Temperature	Saline test method (NSS ACSS) 47±1 °C / Corrosion Test (CASS)63±1 °C		
Lab Capacity (L)	270	480	640
Saline Capacity(L)	25	40	40
Saline Concentration	5% concentration of NaCl, or every Liter 5% NaCl add 0.26g CuCl2H2O		
Compressed Air Pressure	1.0~6.0 Kgf		
Spray Volume	1.0~2.0ml /80cm2 /h(working at least 16 hours, and take the average value)		

**Pictures for reference:**

